

Company		EPDM Coatings	Company A	Company B	Company C
Coverage Rate		80-100 sf/gal	20sf/gal	Metal 70-100ft after applied over KS basecoat	71 sf/gal
Primer Needed		No	Not Provided	Yes	Yes
# Of Coats Required		1	4 - 5	2	1
Weight (lb./gal.)		8.5	Not Provided	Not Provided	10.2
Viscosity @ 78		2900 cps.	Not Provided	Not Provided	
Drying Time		2 - 4 hours	24 - 48 hours	24 hours between coats	Not Provided
Elongation	ASTM-D-412	500%	1500%	Not Provided	315%
Tensile Strength	ASTM-D-412	1520 PSI	180 psi	Not Provided	250 psi
Permeance (10 mils)	ASTM-E-96	0.166 perms	Not Provided	Not Provided	Not Provided
Fungi Resistance	ASTM G 21	0 (Pass)	Not Provided	Not Provided	Not Provided
Water Swell	ASTM D 471	0%	Not Provided	Not Provided	Not Provided
Weathering	ASTM 4798	Pass	Not Provided	Not Provided	Not Provided
Low Temp. Flex	ASTM D 522	Pass	Not Provided	Not Provided	Not Provided
Wind Driven Rain	TT-C-555B	Pass	Not Provided	Not Provided	Not Provided

(ASTM C 794/D 903) WET ADHESION Test On The Following Roof Types

		EPDM Coatings	Company A	Company B	Company C
Metal		Pass	Not Provided	Not Provided	Not Provided
SBS Mod. Bit.		Pass	Not Provided	Not Provided	Not Provided
APP Mod. Bit.		Pass	Not Provided	Not Provided	Not Provided
Smooth BUR		Pass	Not Provided	Not Provided	Not Provided
EPDM		Pass	Not Provided	Not Provided	Not Provided
TPO		Pass	Not Provided	Not Provided	Not Provided
Hypalon		Pass	Not Provided	Not Provided	Not Provided
SPUF (Foam)		Pass	Not Provided	Not Provided	Not Provided